



## DENSCAL® ST

### General Recommendation for Use:

Use Consistency (cc/100gms)	30
Vicat Set Time (minutes)	15 - 25
% Set Expansion	0.2
Dry Density (lbs. / ft <sup>3</sup> )	110.8
Expected Compressive Strength (PSI)	11,000

\*Measured at Use Consistency

\*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

### **Description:**

G-P Gypsum's strongest and hardest Denscal gypsum cement, recommended for applications requiring high surface hardness. ST is a viscous pouring material, excellent for solid patterns, models, and molds.

**For more information, call 1-888-PLASTER.**