



## K-60™ POTTERY PLASTER

### General Recommendation for Use:

Use Consistency (cc/100gms)	67
Vicat Set Time (minutes)	25 - 35
% Set Expansion	0.18
Dry Density (lbs. / ft <sup>3</sup> )	70 - 72
Expected Compressive Strength (PSI)	2100 - 2300

\*Measured at Use Consistency

\*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

### **Description:**

A fine grind, high purity, white plaster used in making molds for vitreous china and clay pottery.

**For more information, call 1-888-PLASTER.**