

**DENSCRETE® EXTERIOR STATUARY****General Recommendation for End Use @ 1: 1 Sand to Cement Ratio**

Use Consistency (cc/100gms of sanded mix)	15
Dry Density (lbs. / ft ³)	approx. 141.5
% Set Expansion	
Difference in Length between 1 day and 14 day:	0.031
Difference in Length between 1 day and 28 day:	0.041
Difference in Length between 1 day and 56 day:	0.054
% Length Change	
7 day Length Change:	- 0.203
14 day Length Change:	- 0.249
28 day Length Change:	- 0.250
56 day Length Change:	- 0.280

Resistance of Concrete to Rapid Freezing and Thawing Average

Cycles Completed	Weight Change	Relative Dynamic Modulus
314	+ 1.8 grams	95.2%

Age	Average Compressive Strength (PSI)
1 hour	250
3 hour	1210
5 hour	1240
24 hour	1350
3 days	5590
28 days	10150

*Measured at Use Consistency and a Sand to Cement of 1:1.

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of sanded mix.

*Product is not intended to be used without sand. Best performance can be obtained with sand to cement ratio of 1:1 minimum.

*Vicat Set Time of cement before blending with sand can be adjusted to suit customer needs.

Description:

Fast setting cement intended for exterior statuary such as birdbaths or similar decorative applications/products.

For more information, call 1-888-PLASTER.