



K-58™ POTTERY PLASTER

General Recommendation for Use:

Use Consistency (cc/100gms)	70
Vicat Set Time (minutes)	25 - 35
% Set Expansion	0.15
Dry Density (lbs. / ft ³)	69 - 71
Expected Compressive Strength (PSI)	2000 - 2200

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

A fine grind, high purity, white plaster with a Thermal Shock additive used in making molds for vitreous china and clay pottery.

For more information, call 1-888-PLASTER.