



SUNFLOWER MOLDING PLASTER

General Recommendation for Use:

Use Consistency (cc/100gms)	70 - 80
Vicat Set Time (minutes)	27 - 35
% Set Expansion	0.17 - 0.19
Dry Density (lbs. / ft ³)	69 - 71
Expected Compressive Strength (PSI) (1 Hour After Set)	1000 - 1100
Expected Compressive Strength (PSI) (Dry)	2100 - 2400

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

Excellent all purpose plaster used in applications where strength, hardness and expansion are not critical.

Meets ASTM designation C59.

For more information, call 1-888-PLASTER.