



## K-62™ POTTERY PLASTER

### General Recommendation for Use:

Use Consistency (cc/100gms)	66
Vicat Set Time (minutes)	20 - 30
% Set Expansion	0.2
Dry Density (lbs. / ft <sup>3</sup> )	71 - 73
Expected Compressive Strength (PSI)	2200 - 2400

\*Measured at Use Consistency

\*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

### **Description:**

A high speed pottery plaster for use in making molds for high speed jiggering machines for making china cups, bowls, and power line insulators.

**For more information, call 1-888-PLASTER.**