

G-P Gypsum

a Georgia-Pacific company



Ultra Statuary (BR745)

General Recommendation for Use:

Pouring Consistency (cc/100gms)	66 - 68
Vicat Set Time (minutes)	25 - 35
% Set Expansion	0.20 - 0.25
Dry Density (lbs. / ft ³)	70 - 72
Expected Compressive Strength (PSI) (Dry Cube @ Pouring Consistency)	1500 - 2000

*Measured at Pouring Consistency

*Pouring Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product to obtain patty diameter of 6 inches $\pm\frac{1}{4}$ ".

Description:

A fiber reinforced Statuary plaster.

For more information, call 1-888-PLASTER.